





*The Fire element
represents passion,
creativity & spontaneity.
Sagittarians are keen to
have things revolve
around themselves to
keep the energy high.*





Elevation A

Elevation B



Layout Plan of Toilet Cubicle

General Specifications

The Toilet Partition shall be **ATOZ SAGITTARIUS System**.

This a hybrid of floor mounted & ceiling types that promise absolute stability and durability.

All cubicles shall be fitted with 304 Grade Hairline Finished Stainless Steel standard accessories. The partitions shall be using 100% water resistant and chemical resistant compact laminate impregnated with melamine resins pressed over kraft paper impregnated with phenolic resins.

Recommended Thickness of Partitions

All cubicle doors, pilasters & intermediate partitions shall be using 12mm or 19mm thick HPL Compact Board with chamfered edge.

Fabrication

Doors shall be supported by 3 or more hinges affixed to the pilaster, one with a built-in adjustable spring for automatic door closing or for holding the door open; with fixed coat hook & door knob on the inner side of the door.

Door of standard cubicles shall be in-swinging with clearance width of min. 600mm; Out-swinging doors for ambulant cubicles with clearance width of min. 800mm.

The pilasters are anchored onto the tiled floor using 25mmH Anodised Aluminium Extruded U-Channel.

The top of the pilasters shall be mounted with anodised aluminum U-channel concealed above the false ceiling. Pilasters shall be routed at vertical side to facilitate door closure, and completed with door Thumbturn lockset with occupancy indicator & emergency release.

Intermediate partitions shall be fixed with aluminium U-Channel Section affixed at the ends to the wall and pilaster. Recommended depth not exceeding 1800mm for stability.

Finishes


Panels available in standard solid plain colours with smooth finishes on both sides.

Restroom Cubicle Compartment Dimension

Cubicle Size: 800 – 900mmW Front


Divider Panel: 1500 – 1800mmD Intermediate

Overall Height: 2400 – 2700mmH



TECHNICAL DATA

Physical Properties of Compact® Grade Laminate.



PROPERTY	TEST METHOD EN 438-2:2016	PROPERTY OR ATTRIBUTE	UNIT	MIN. TEST STANDARDS	FORMICA TYPICAL VALUE (CGS)
Resistance to Surface Wear	EN 438-2/10	Wear Resistance	Revolution	350	500
Resistance to Immersion in Boiling Water	EN 438-2/12	Mass Increase	%	<2	0.53
		Thickness Increase	%	<2	0.58
		Appearance: Surface	Rating	4	5
		Edge	Rating	3	5
Resistance to Water Vapour	EN 438-2/14	Appearance	Rating	4	5
Resistance to Dry Heat	EN 438-2/16	Appearance	Rating	4	5
Dimensional Stability at Elevated Temperature	EN 438-2/17	Cumulative Dimensional Change:			
		Dry Heat (Machine Direction)	%	<0.3	0.06
		Dry Heat (Cross-machine Direction)	%	<0.6	0.06
		High Humidity (Machine Direction)	%	<0.6	0.09
		High Humidity (Cross-machine Direction)	%	<0.6	0.06
Resistance to Wet Heat (100°C)	EN 438-2/18	Appearance	Rating	4	5
Resistance to Impact by Large Diameter Ball	EN 438-2/21	Drop Height	mm	1800	2000
Resistance to Crazeing Test	EN 438-2/24	Appearance	Rating	4	5
Resistance to Scratching	EN 438-2/25	Force	Rating	3	3 (2N)
Resistance to Staining	EN 438-2/26	Appearance	Rating	4	5
Light Fastness (Xenon Arc)	EN 438-2/27	Contrast	Rating	4-5	4-5



PROPERTY	TEST METHOD	UNIT	MIN. TEST STANDARDS	FORMICA TYPICAL VALUE (CGS)
Tensile Strength	ISO 527-2:2012	MPa	60	96.57
Flexural Strength	ISO 178:2010	MPa	80	161.14
		MPa	9000	10615
Density	ISO 1183-1:2012	g/cm ³	1.35	1.44

* Technical data is accurate at the time of printing. Data is subjected to change without prior notice.
* Rating 5 is the best. Rating 1 is the worst.